



DESCRIPTION

Single component non-yellowing vinyl resin based sealer for wood floors. Its fast drying time makes it suitable for carrying out quick finishing cycles. V 15 has been specifically formulated to be overcoated with single component solvent based polyurethane finishes, but it is also recommended for all those cycles in which the colour change of the floor has to be limited. V 15 also has a significant water-repellent action.

10 Lt

TECHNICAL DATA CHEMICAL-PHYSICAL CHARACTERISTICS at 20°C (indicative values not constituting product specifications):	
Completely dry (minutes)	30
Overcoating (minutes)	30
Application method	Roller, Brush
Average coverage per coat (g/m ²)	80/100
Adhesion (checkering)	100%
Stability and storage (in original, unopened containers stored in a cool, dry place) (months)	12
Calculated VOC (g/ltr)	750
Max permitted dilution (EC Dir.2004/42)	None
To clean tools	SOLVENTE LAVAGGIO
Standard packaging (Lt)	2x10

APPLICATION

First the floor must be sanded, filled with Vermeister binders for solvent based fillers and then vacuumed carefully. Apply one coat of V 15 following the recommended quantities (80/100 g/m²). After about 30 minutes, the floor can be sanded with a fine grit sandpaper (220/320) or alternatively with abrasive felt and then the subsequent coats of finish can be given. The sanding operation can be avoided.

NOTES

Do not overcoat directly with waterborne finishes, except for the finishing cycles on Color.Oil White and Grey.
(See the guide for use of Color.oil)
Stir well before use.
Product subject to the restrictions prescribed by EC Dir.2004/42.

Safety precautions Keep the product in a tightly closed, upright container in a cool place away from sources of heat. The product is classified and coded in compliance with EC Directives/regulations concerning hazardous substances. The information for the user is given in the relevant safety sheet. Empty containers or those containing slight traces of the product must be disposed of in accordance with local regulations. VerMeister S.p.A. guarantees that the details given in this sheet are provided to the best of the company's technical-scientific knowledge and experience; however, the company cannot be held responsible in any way for the results obtained with the products as the conditions of application are beyond the company's control. It is always advisable to check the suitability of the product to each specific circumstance. This sheet cancels and replaces all previous editions.